

Visit our web site:
<http://www.ariindustries.com>
E-Mail: sales@ariindustries.com



ARI Industries Inc

381 ARi Court
Addison, IL 60101
630-953-9100 Tel
630-953-0590 Fax



AerOseal®

Part Number 61226-2 & 61226-3

AerOseal® is a specially formulated liquid that prevents penetration of moisture into ceramic insulations. It is effective on magnesium oxide, aluminum oxide and similar materials used in thermocouples, metal-sheathed conductors, electrical heating elements and ceramic electronic components. Through diffusion, AerOseal® forms a positive moisture barrier, yet permits the coated part to "breathe".

AerOseal® is a clear, colorless, inorganic liquid of a proprietary, patented composition. It is non-toxic and contains no boron or equivalent nuclear poisons and is essentially harmless.

When applied properly, the seal is effective over the temperature range of -240 to +420°C (-400 to +788°F). It can withstand thermal shock from +420°C (788°F) to -185°C (-300°F) in 2 seconds. Exposure to temperatures above +420°C (788°F) will cause the seal to deteriorate without affecting insulation resistance properties.

The shelf life of AerOseal® is indefinite if cap is kept securely closed while not in use.

Directions for Use:

1. Heat part to be sealed at 400°F for a minimum of three hours to remove all traces of moisture.
2. Remove from oven and immerse immediately in AerOseal°. Soak entire part for at least four hours.
3. After soaking, heat part in circulating air over at 500°F for a minimum of five hours.
4. It is recommended that normal Volatile fume precautions be taken when performing step 3. A well ventilated air circulating oven, preferably of the forced draft type should be used.